

Retro Active

PORCELAIN STONE

- Available in classic eight colors
- Two finishes, unpolished and polished
- Tile sizes of 3"x12", 4"x12", 6"x6" and 6"x12"
- Coordinating trim in the unpolished finish only.

- Ideal for minimalist design schemes in commercial and upscale residential spaces
- All the performance attributes of Porcelain Stone® with the aesthetics and the versatility to make it a design favorite.



RPW1 Pure White UPS



A215 Empress White PO/UPS



A870 Seal Taupe PO/UPS



A890 Ebony PO/UPS



B110 Antico Taupe PO/UPS



B210 Seabreeze PO/UPS



C360 Maple Sugar PO/UPS



C370 Featherstone PO/UPS

Sizes Available

Nominal Size	Actual Size	Thickness
3" x 12"	2-3/4" x 11-3/4"	5/16"
4" x 12"	3-3/4" x 11-3/4"	5/16"
6" x 6"	5-3/4" x 5-3/4"	5/16"
6" x 12"	5-3/4" x 11-3/4"	5/16"


* Custom cut program. Allow 2-4 weeks for delivery.

Trim Sizes (Available in all colors)

4" x 12" Single Bullnose PO & UPS	3-3/4" x 11-3/4"	5/16"
2" x 12" Cove Base UPS	1-3/4" x 11-11/16"	3/8"
2" x 2" Cove Base Inside Corner UPS	1-3/4" x 1-3/4"	3/8"
2" x 4" Cove Base Outside Corner UPS	1-3/4" x 3-1/2"	3/8"



4" x 12" Single Bullnose



2" x 12" Cove Base



2" x 2" Inside Cove Base Corner



2" x 4" Outside Cove Base Corner

Shade & Texture Index

Retro Active has a shade variation of V1



V1



V2



V3



V4

V1=Uniform Appearance
V2=Slight Variation
V3=Moderate Variation
V4=Substantial Variation

Recommended Usage

Retro Active is recommended for interior floors, walls and countertops and exterior walls in both residential and commercial applications.

Care and Maintenance

Regular cleaning is the best way to keep Retro Active tile looking good for years to come. Use clean, hot water (combined with a household cleaner for more aggressive cleaning). Rinse thoroughly and dry with a soft cloth to prevent water spots. No waxes or sealers are needed. More information regarding the care and maintenance of Crossville products is available at www.crossvilleinc.com.

Product Performance

Abrasive Wear	270-330	ASTM C501
Breaking Strength	350-420 lbf.	ASTM C648
Bond Strength	>200 psi	ASTM C482
Chemical Resistance	Unaffected	ASTM C650
Frost Resistance	Resistant	ASTM C1026
Water Absorption	<0.10%	ASTM C373
Scratch Hardness	6	MOH's Scale
COF-UPS Dry	>0.7	ASTM C1028
COF-UPS Wet	>0.6	ASTM C1028
COF-PO Dry	>0.7	ASTM C1028
COF-PO Wet	>N/A	ASTM C1028



Retro Active
Wall: A215 Empress White 4" x 12" UPS, A870 Seal Taupe 4" x 12" UPS,
B110 Antico Taupe 4" x 12" UPS
Floor – A890 Ebony 4" x 12" UPS

Crossville, Inc. • P.O. Box 1168, Crossville TN 38557
Phone: 931.484.2110 • Fax: 931.456.2956
E-mail: crossc@crossvilleinc.com • www.crossvilleinc.com

