


Wood Impressions

PORCELAIN STONE

- Beautifully durable alternative to wood
- Variety of plank sizes add design versatility
- Suitable for residential and commercial applications


- Virtually maintenance free with a lifetime of beauty
- Made in U.S.A.



AV191 Willow



AV192 Birch



AV193 Barnwood Gray



AV194 Gunstock

Sizes Available (Available in all colors)



Sizes Available

Nominal	Actual (mm)	Thickness (mm)
3 x 3 Mosaics*	72 x 72	10.5
3 x 18	72 x 447	10.5
6 x 6	147 x 147	10.5
6 x 12	147 x 297	10.5
6 x 18	147 x 447	10.5
6 x 36	147 x 897	10.5

*Mounted on 11-3/4 x 11-3/4 sheets
All sizes are rectified and modular with a 3mm grout joint.

Coordinating Trim (Available in all colors)


3 x 18 Single Bullnose	72 x 447	10.5
------------------------	----------	------




3" x 18" Single Bullnose

Shade & Texture Index


Wood Impressions has a shade variation of V2



V1=Uniform Appearance
V2=Slight Variation
V3=Moderate Variation
V4=Substantial Variation



AV195 Brazilian Cherry



AV196 Black Walnut

Care and Maintenance

Regular cleaning is the best way to keep Wood Impressions tile looking good for years to come. Use clean, hot water (combined with a household cleaner for more aggressive cleaning). Rinse thoroughly and dry with a soft cloth to prevent water spots. No waxes or sealers are needed. More information regarding the care and maintenance of Crossville® products is available at www.crossvilleinc.com.

Recommended Usage

Wood Impressions is recommended for interior floors, walls and countertops and exterior walls in both residential and commercial applications. If offset is required for rectangles longer than 12 inches, Crossville® recommends an offset of not greater than 33%. See crossvilleinc.com for detailed installation instructions.

Product Performance

Breaking Strength	>450 lbf.	ASTM C648
Bond Strength	>200 psi	ASTM C482
Chemical Resistance	Unaffected	ASTM C650
Frost Resistance	Resistant	ASTM C1026
Water Absorption	<0.10%	ASTM C373
Scratch Hardness	7	MOH's Scale
Coefficient of Friction		
Dry	>0.7	ASTM C1028
Wet	>0.6	ASTM C1028





Wood Impressions
Floor: AV195 Brazilian Cherry 6" x 6", 6" x 12" and 3" x 18"

Crossville, Inc. • P.O. Box 1168, Crossville TN 38557
Phone: 931.484.2110 • Fax: 931.456.2956
E-mail: crossc@crossvilleinc.com • www.crossvilleinc.com

 CROSSVILLE.